

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
29 March 2001 (29.03.2001)

PCT

(10) International Publication Number
WO 01/22518 A1


- (51) International Patent Classification: **H01M 10/40** (74) Agent: STOLK, Steven, A.; Internationaal Octrooibureau B.V., Prof Holstlaan 6, NL-5656 AA Eindhoven (NL).
- (21) International Application Number: **PCT/EP00/08974** (81) Designated States (national): CN, JP, KR.
- (22) International Filing Date:
13 September 2000 (13.09.2000) (84) Designated States (regional): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
99203098.1 22 September 1999 (22.09.1999) EP
- (71) Applicant: **KONINKLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]**; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).
- (72) Inventors: **HIKMET, Rifat, A., M.**; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). **FEIL, Hans**; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).

Published:

- With international search report.
- Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **LITHIUM SECONDARY BATTERY COMPRISING INDIVIDUAL CELLS CONNECTED WITH ONE ANOTHER, AS WELL AS WATCHES, COMPUTERS AND COMMUNICATION EQUIPMENT PROVIDED WITH SUCH A BATTERY**



(57) Abstract: A lithium secondary battery (5) comprising individual cells connected with one another, which cells comprise a negative electrode including negative electrode material (9) and a negative current collector (7), a positive electrode including positive electrode material (10) and a positive current collector (8), a separator (6) sandwiched between the negative and the positive electrode, a non-aqueous electrolyte solution between the negative and the positive electrode, the negative and the positive electrode material being provided in segments on the respective current collector in order to increase the pliability of the battery. The present battery is characterized by the use of a common current collector (7, 8) for all individual cells connected with one another.

WO 01/22518 A1

Lithium secondary battery comprising individual cells connected with one another, as well as watches, computers and communication equipment provided with such a battery.

The invention relates to a lithium secondary battery comprising individual cells connected with one another, which cells comprise

- a negative electrode comprising a negative electrode material and a negative current collector,
 - 5 - a positive electrode comprising a positive electrode material and a positive current collector,
 - a separator provided between the negative and the positive electrode,
 - a non-aqueous electrolyte solution between the negative and the positive electrode,
- wherein

10 both the negative and the positive electrode material is provided in segments on the respective current collector to increase the pliability of the battery.

The invention further relates to certain applications of such a battery, in which applications demands are made on, in particular, the pliability of the battery, such as in watches and communication equipment, for example portable computers, personal digital assistants and
15 mobile telephones.

Such a lithium secondary battery composed of individual cells connected with one another is known from United States patent specification 4,092,464. In accordance with the battery disclosed in said document, the active electrode material can be provided in segments on the current collector to increase the flexibility of the battery, which means that
20 the stress developed during bending is concentrated at the locations between the active segments of the current collector. Such a cell is manufactured from a lithium anode folded around a silver-chromate cathode, the anode and the cathode being separated from each other by a porous polypropene separator which extends beyond the dimensions of the cathode material. Since the polypropene used as the separator is a thermoplastic microporous
25 material, this material, when heated, is capable of enclosing the cathode, whereby only one connection element is left uncovered. Around the lithium anode there is a second layer of polypropene, which layer extends at the circumference of the lithium anode and is sealed by heating, thereby enclosing both the lithium anode and the envelope containing the silver-chromate cathode, whereby only connection points for anode and cathode are exposed. The

anode terminal is brought about via a metal strip formed by means of spot welding on the expanded current collector. A similar external electric connection with the cathode is also obtained by providing a metal strip on the cathodic current collector by means of spot welding. Finally, the anode and cathode strips are provided with a coating enabling the
5 formation of a durable seal with respect to the outermost cell envelope. To attain a larger current capacity, such cells are arranged in parallel, whereby the external electrical connection points should be connected with one another. It has been found in practice that such connection points adversely affect the durability of a lithium secondary battery composed of individual cells connected with one another. In addition, the electrical resistance
10 increases, which also adversely affects the efficiency of such a battery.

A lithium secondary battery comprising individual cells connected with one another is also known from United States patent specification 5,872,744. This United States patent specification does not teach, however, to provide both the negative and the positive electrode material in segments on the respective current collector to increase the pliability of
15 the battery.

It is an object of the invention to provide a lithium secondary battery comprising individual cells connected with one another, which battery obviates the above-mentioned drawbacks in accordance with the state of the art.

Another object of the invention is to provide a lithium secondary battery
20 comprising individual cells connected with one another, which battery is provided with electrode materials disposed in segments on the respective current collectors, such that the pliability of the eventual battery takes place in two dimensions.

A further object of the invention is to provide a lithium secondary battery comprising individual cells connected with one another, which battery does not exhibit
25 delamination of the negative electrode, the positive electrode and the separator.

Yet another object of the invention is to provide a lithium secondary battery which can be manufactured in a thin and flexible form and wherein the contact between the electrodes and the electrolyte is maintained in a particular way.

A further object of the invention is to provide a battery which can suitably be
30 used in an application which is subject to bending and corrugation, and wherein there are no restrictions as regards the geometrical configuration wherein the battery is incorporated.

The lithium secondary battery mentioned in the preamble is characterized, in accordance with the invention, in that the individual cells are interconnected by means of a current collector which is common to all cells.

As a result of the use of a common current collector for all cells, the individual cells do not have to be interconnected via external connection points. In addition, the common current collector endows the relevant lithium secondary battery with sufficient flexibility, so that this battery can suitably be used in applications wherein pliability and bendability are required, particularly in wrist watches and communication equipment which is worn around the wrist.

In a particular embodiment of the lithium secondary battery, preferably, both the negative and the positive current collector serves as a common current collector for every cell.

The use of both the negative and the positive current collector as a common current collector for all cells provides the battery with additional power, so that long-term durability is guaranteed.

In another, preferred embodiment, the mutual connection between the individual cells in the lithium secondary battery is also brought about by means of a common separator for all cells.

In such a particular embodiment of the invention, both the separator and one or both current collectors are the same for every cell. In a particular embodiment of the relevant lithium secondary battery it is thus possible that the lithium secondary battery composed of individual cells connected with one another comprises a common negative current collector, a common positive current collector, and a common separator.

To obtain the desired pliability of the battery, it is preferred in a particular embodiment that the electrode material provided in segments on the current collector extends substantially throughout the width of the relevant current collector.

In accordance with such an embodiment, in fact, pliability in one dimension is obtained, the desired pliability being obtained at locations where there is no active electrode material.

If, however, pliability of the battery in two dimensions is desired, it is preferred that the electrode material provided in segments on the current collector is situated on the relevant current collector in accordance with a chessboard-like pattern.

The term "chessboard-like pattern" as used in the description should be construed as a pattern of active electrode material, such that each segment of active electrode material does not border on another segment of active electrode material. As a result, discrete segments of active electrode material are situated on the current collector, so that the desired pliability in two dimensions is obtained.

In the lithium secondary battery in accordance with the invention, preferably carbon or graphite is used as the negative electrode material.

The positive electrode material used in the relevant battery is preferably selected from lithium transition metal oxides, such as LiMn_2O_4 , LiCoO_2 or LiNiO_2 , which
5 material comprises electroconductive particles, such as carbon or graphite, and possibly binder material. Such positive electrode material may be considered to be a lithium-intercalation compound. The quantity of conductive material lies in the range from 0.1 to 15% by weight.

To obtain a lithium secondary battery which can be manufactured so as to be
10 thin and flexible, preferably, the contact between the electrodes and the electrolyte is maintained in a specific manner, more particularly in that the negative electrode material, the positive electrode material and the separator are preferably provided with a pattern of apertures, said apertures being filled with a polymer-like material which holds together the negative electrode, the positive electrode and the separator.

15 Such a construction is described in international patent application WO 99/04716, which was filed by the current applicant but is not yet laid open to public inspection, which document is considered to be incorporated herein. The apertures in the electrode materials are macroscopic apertures having a diameter of approximately 1 mm. In accordance with a particular embodiment, the pattern of the apertures forms a rectangular
20 two-dimensional arrangement with an interspace between the apertures of 5 mm. The dimensions of the apertures and the pattern are selected to be such that the active surface of the electrodes is preferably at least 90%, because the apertures filled with polymer-like material reduce the capacity of the electrodes, which can be attributed to the fact that the active electrode material is absent in these filled apertures.

25 As described hereinabove, the positive electrode material is a lithium-intercalation compound, which compound is dispersed in a polymeric binder matrix. As the polymers for the binder matrix use is made of thermoplastic polymers, including polysaccharide and polymers with rubber elasticity. Examples hereof include carboxymethyl cellulose, polytetrafluoroethene, polyethene, polypropene and styrene butadiene rubber.
30 These polymers can be applied either individually or in combination with each other. The polymeric binder serves to bind together active material powders to preclude crack formation and to fix such powderous materials on the surface of the current collector. The quantity of polymeric binder lies in the range from 2 to 30% by weight.

For the current collector use can be made of any electric conductor unless a chemical reaction is induced in the battery. Examples of materials for the positive current collector (cathode) include stainless steel, aluminum and nickel. Examples of materials for the negative current collector (anode) include stainless steel, copper and nickel. The collector
5 may be in the form of a foil, a film and a thin plate, which may be porous, punched or in the form of a network. The thickness of the collector generally ranges from 1 to 500 μm .

The separator provided between the positive and the negative electrode is an insulating film having both a high ion permeability and the desired mechanical strength. The separator prevents short-circuits between the negative and the positive electrode and
10 preserves the electrolytic solution. A generally applied separator is made from glass fiber, or is the form of a porous plate of non-woven fabric manufactured from olefin-like polymers, such as polyethylene or polypropene. The diameter of the pores generally ranges from 0.01 to 10 μm . The thickness of the separator generally ranges from 5 to 300 μm .

The battery structure in accordance with the invention can be activated with a
15 number of compositions applied as liquid electrolyte solutions. For the solvent use can be made of an ester compound, such as ethylene carbonate, propylene carbonate, methylethyl carbonate, an ether compound, such as tetrahydrofuran, dimethylsulphoxide and mixtures thereof. Examples of the dissolved electrolyte comprise salts of lithium ions (Li^+) and Lewis acid ions (PF_4^- , PF_6^- , AsF_6^- , ClO_4^- , CF_3SO_3^-) and mixed salts thereof. The concentration of the
20 salt generally ranges between 0.5 and 2 mol/l.

The battery in accordance with the invention is enclosed in a battery envelope, which may be a synthetic envelope, or a metal-like or resin-like envelope. Examples of such materials include stainless steel and plastics such as polypropene. Sealing can be brought about by means of an adhesive, or by welding or soldering. A flat flexible battery may be
25 enclosed in an air and moisture-resistant envelope of polymer-covered aluminum foil. Such foils are commercially available and can be sealed at the edges.

The lithium secondary battery comprising individual cells connected with one another, in accordance with the invention, comprises, preferably, a stack of cells which comprise a negative electrode, a positive electrode, a separator and a non-aqueous electrolyte.

30 The invention further relates to the particular application of the batteries described hereinabove, the battery in question being employed, in particular, in applications imposing high demands as regards pliability, durability and current efficiency. Particularly, preferred applications include, inter alia, watches, whereby the battery is incorporated in the

strap of the watch, communication equipment, such as portable telephones, and portable computers.

These and other aspects of the invention will be apparent from and elucidated with reference to the embodiments described hereinafter.

5

Fig. 1 diagrammatically shows an electrode 1 which is segmented on both sides, and a current collector 2 which is provided with active electrode material 3 on the lower side as well as the upper side, said active electrode material 3 provided on the current collector 2 extending substantially throughout the width of the current collector 2. By virtue of the fact that the active electrode material 3 is provided in segments on the current collector 2, it is possible to bend the electrode 1 without delamination of active electrode material 3 and current collector 2.

Fig. 2 diagrammatically shows an electrode 4 which is segmented on both sides, the active electrode material 3 being provided on both sides of the current collector 2 in accordance with a chessboard-like pattern. An electrode 4 embodied in this manner can be bent in two dimensions because the active electrode material 3 is present in discrete islands on the current collector 2.

Fig. 3 diagrammatically shows a battery 5 composed of three individual segments or cells, both the current collector 7, 8 and the separator 6 being embodied so as to be common to all cells, and each cell being built up of, in succession, a current collector 8, active electrode material 10, a separator 6, active electrode material 9 and a current collector 7. At the location referenced 11 there is no active electrode material 9, 10, so that a battery 5 can be readily bent at this location.

Finally, Fig. 4 diagrammatically shows the battery 5 of Fig. 3 in a bent state, and it is obvious from said Figure that bending is not hampered owing to the fact that the active material 9, 10 is present in segments.

Example

A battery to be integrated in a wrist strap of a communication device which looks like a wrist watch is manufactured, the battery being composed of a stack of two positive electrodes segmented on one side, a positive electrode segmented on both sides, and two negative electrodes segmented on both sides, said electrodes being separated by separators. For the active electrode material use is made in the positive electrode of LiCoO_2 , while the active electrode material of the negative electrode is MCMB (Meso Carbon Micro

Beads having a diameter of 10 μm). The separator is made from microporous polyethylene. The battery has a width of 1 cm, a length of 10 cm and an overall thickness of approximately 1 mm, and is composed of 10 segments or cells, so that a sufficiently pliable battery is obtained. The capacitance of the battery is approximately 100 mAh.

CLAIMS:

1. A lithium secondary battery comprising individual cells connected with one another, which cells comprise
a negative electrode comprising a negative electrode material and a negative current collector,
5 - a positive electrode comprising a positive electrode material and a positive current collector,
- a separator provided between the negative and the positive electrode,
- a non-aqueous electrolyte solution between the negative and the positive electrode,
wherein
both the negative and the positive electrode material is provided in segments
10 on the respective current collector to increase the pliability of the battery, characterized in
that the individual cells are interconnected by means of a current collector which is common
to all cells.
2. A lithium secondary battery comprising individual cells connected with one
15 another, as claimed in claim 1, characterized in that both the negative and the positive current
collector serves as a common current collector for every cell.
3. A lithium secondary battery comprising individual cells connected with one
another, as claimed in claim 1 and 2, characterized in that the mutual connection between the
20 individual cells is also brought about by means of a common separator for all cells.
4. A lithium secondary battery comprising individual cells connected with one
another, as claimed in claims 1 to 3, characterized in that the electrode material provided in
segments on the current collector extends substantially throughout the width of the relevant
25 current collector.
5. A lithium secondary battery comprising individual cells connected with one
another, as claimed in claims 1 to 3, characterized in that the electrode material provided in

segments on the current collector is situated on the relevant current collector in accordance with a chessboard-like pattern.

6. A lithium secondary battery comprising individual cells connected with one another, as claimed in claim 1, characterized in that carbon or graphite is used as the negative electrode material.

7. A lithium secondary battery comprising individual cells connected with one another, as claimed in claim 1, characterized in that the positive electrode material is selected from lithium transition metal oxides, such as LiMn_2O_4 , LiCoO_2 or LiNiO_2 , which material comprises electroconductive particles, such as carbon or graphite, and possibly binder material.

8. A lithium secondary battery comprising individual cells connected with one another, as claimed in claims 1 to 7, characterized in that the negative electrode material, the positive electrode material and the separator are provided with a pattern of apertures, said apertures being filled with a polymer-like material which holds together the negative electrode, the positive electrode and the separator.

9. A lithium secondary battery comprising individual cells connected with one another, as claimed in claim 8, characterized in that the polymer-like material is a bonding agent.

10. A lithium secondary battery comprising individual cells connected with one another, as claimed in claim 8, characterized in that the polymer-like material is polyethene.

11. A lithium secondary battery comprising individual cells connected with one another, as claimed in claims 1 to 10, characterized in that the individual cells are provided in an envelope of a laminate, which envelope is hermetically sealed.





12. A lithium secondary battery comprising individual cells connected with one another, as claimed in claims 1 to 11, characterized in that the cell is composed of a stack of cells comprising a negative electrode, a positive electrode, a separator and a non-aqueous electrolyte.

13. A watch provided with a battery, characterized in that the battery is applied as claimed in claims 1 to 12.

5 14. A communication device provided with a battery, characterized in that the battery is applied as claimed in claims 1 to 12.

15. A computer provided with a battery, characterized in that the battery is applied as claimed in claims 1 to 12.

1/1



INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 00/08974

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 H01M10/40

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

PAJ, EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 498 489 A (DASGUPTA SANKAR ET AL) 12 March 1996 (1996-03-12) column 4, line 13 -column 5, line 24 column 6, line 12 -column 7, line 22; claims 1-15	1-4,6,7, 11,12
X	US 5 911 947 A (MITCHELL NATHAN) 15 June 1999 (1999-06-15) column 2, line 40 -column 4, line 58; claims 1-14 --- -/--	1-4,6,7, 11,12, 14,15



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

A document member of the same patent family

Date of the actual completion of the international search

29 January 2001

Date of mailing of the international search report

05/02/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel: (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

De Vos, L

Intern. Appl. Application No
PCT/EP 00/08974

1

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/08974

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 015, no. 159 (E-1059), 22 April 1991 (1991-04-22) & JP 03 030260 A (SHIN KOBE ELECTRIC MACH CO LTD), 8 February 1991 (1991-02-08) abstract	1-3
A	WO 97 15959 A (MEYER ANDREAS FELIX ;SONCEBOZ EBAUCHES FAB (CH); MEYER TOBIAS BALT) 1 May 1997 (1997-05-01) page 4, line 27 -page 5, line 30 page 8, line 25-36; claims 7-15	1-10,13

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 00/08974

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5498489	A	12-03-1996	CA 2169484 A,C DE 19540845 A FR 2727572 A GB 2298309 A,B	15-10-1996 09-05-1996 31-05-1996 28-08-1996
US 5911947	A	15-06-1999	NONE	
EP 0614237	A	07-09-1994	JP 6215753 A JP 6267581 A JP 6267527 A JP 6267526 A JP 6333551 A JP 7057708 A CA 2113372 A DE 69403246 D DE 69403246 T US 5547780 A	05-08-1994 22-09-1994 22-09-1994 22-09-1994 02-12-1994 03-03-1995 19-07-1994 26-06-1997 09-10-1997 20-08-1996
US 5525441	A	11-06-1996	US 5618318 A	08-04-1997
US 5776628	A	07-07-1998	US 6120563 A	19-09-2000
JP 60070669	A	22-04-1985	NONE	
EP 0602976	A	22-06-1994	JP 6187998 A AU 675983 B AU 5248393 A DE 69328411 D DE 69328411 T US 5582931 A US 5693105 A	08-07-1994 27-02-1997 30-06-1994 25-05-2000 14-09-2000 10-12-1996 02-12-1997
EP 0025663	A	25-03-1981	AU 536545 B AU 6217880 A BR 8005825 A DE 3067151 D GB 2060983 A,B JP 56048073 A US 4307161 A	10-05-1984 19-03-1981 24-03-1981 26-04-1984 07-05-1981 01-05-1981 22-12-1981
JP 59117073	A	06-07-1984	NONE	
WO 9423465	A	13-10-1994	DE 69404291 D DE 69404291 T EP 0693227 A JP 8508604 T US 5633097 A	21-08-1997 26-02-1998 24-01-1996 10-09-1996 27-05-1997
JP 03030260	A	08-02-1991	JP 2782802 B	06-08-1998
WO 9715959	A	01-05-1997	AU 7209496 A	15-05-1997